## **Specification** (typical values)

PHYSICAL PROPERTIES			
Core material	Super high density recycled post industrial PU foam		
Density (kg/m³)	145		
Top surface	Printed stabilising non-woven fleece bonded by green film		
Bottom surface	Stabilising non-woven fleece bonded by green film		
Nominal thickness (mm)	11.00		
Dimensions (m²)	1.37m x 11.00m = 15.07		
Roll weight (kg)	23.00		

PRODUCT PERFORMANCE - BS EN 14499	RESULTS	STANDARD
Elongation at 30N - length / width (%)	<7.5 / <7.5	- BS EN ISO 13934-1
Breaking strength - length / width (N)	>90.0 / >40.0	
Loss in thickness after long term static loading (%)	<2.5	ISO 3416
Loss in thickness after dynamic loading (%)	< 5.0	BS ISO 2094
Work of compression after dynamic loading (J/m²)	>170	
Retained work of compression (%)	>80	BS 4098 / BS ISO 2094
Compression after dynamic loading (mm)	6.0	
Resistance to cracking	Pass	BS EN 14499
Assessment of wear	No negative effect	BS ISO 1036

OTHER RELEVANT DATA				
Flammability				
Hot metal nut test	Pass - Medium radius of effect	BS 4790 / BS 5287		
Thermal performance				
Thermal resistance (tog)	2.53	BS 4745		
Acoustic performance				
Impact sound reduction (dB)	46	BS EN ISO 10140-3		
USAGE CLASSIFICATION	L/U	Luxury Use		



## Floorwise reference: F9AL/Issue 3/July 2023

1. All values are nominal and may vary within our manufacturing tolerances 2. Some values may have been derived from the testing of similar products







